

# Technical Data Sheet

# **BASADUR® E 202**

Middle coat | High Solid Content | General | 13%

## **Description**

BASADUR® E 202 is a pigmented high solid, epoxypolyamine floor coating. Seamless, Moderate pot life and very good mechanical and physical properties are some of its properties.

#### Uses

It can be used as an intermediate layer in various industries on a well-prepared and primed substrate.

## Also Available from **BASA Polymer**

#### **Primers**

BASADUR® E 101 BASADUR® E 102 BASADUR® E 105 BASADUR® E 112

# **Body Coats / Self** Levels BASADUR® E 303 BASADUR® E 304 BASADUR® E 306

BASADUR® E 307

**Top Coats** BASADUR® E 401 BASADUR® E 402 BASADUR® E 707

#### **Benefits**

- Good mechanical and physical properties
- Hard-wearing
- Low viscosity and Easy application

#### **Technical Information**

Properties	_
Solid Content (%) (ASTM D2369)	~ 99
Mix Ratio by weight	100:13
Pot Life at 27°C (min)	45
Mixed Density (g/cm³) (ISO 2811)	1.9 approx.
Dry-Hard Time (hr.)	8
Recommended Coverage (g/m²)	500 – 1500
Overcoat Time (hr.)	8 - 24
Bond Strength (MPa) (ASTM D4541)	> 1.5 (concrete failure)
Shore D Hardness (ASTM D2240)	87 (after 7 days)

# **Shelf Life**

Maximum 4 months since the date of production.

### Safety information

Please check the MSDS of BASADUR® E 202.

#### **Packaging**

Part A: 22.1 kg containers, 200 kg drums

Part B: 2.9 kg containers, 200 kg drums

# Substrate Requirements and **Preparation**

The substrate's compressional strength should be a minimum of 20 N/mm<sup>2</sup>, and the substrate should be less than 3% moist. The substrate has to be prepared by a suitable mechanical or chemical process to remove any oil, dirt, and residues of alkali compounds. Weak areas of the concrete must be removed completely. You can use BASADUR® products to repair substrate, fill cavities, holes, and cracks. Before applying the coating, remove all dust from the substrate with a vacuum cleaner.

#### **Storage**

The product must be stored in its original packaging in a dry place at a temperature range of 10 to 25 °C.

#### Legal Note

The information, and, in particular, the recommendations relating to the application and end-use of BASADURS, are given in good faith based on BASADURS's current knowledge and experience of the products when properly stored, handled, and applied under normal conditions by BASA's recommendations. In practice, the differences in materials, substrates, and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. BASA Polymer reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

